

### C10200 (Cu-OF)

18 08 US

Comparable standards: UNS C10200 • EN CW008A • JIS C1020

Aurubis designations: C102

#### Description

Oxygen-Free, High Conductivity Copper Cu-OF (99.95 % minimum Cu) offers the advantages of both Electrolytic Tough Pitch Copper (ETP) and Phosphor deoxidized Copper. The high purity and absence of deoxidizers accounts for electrical conductivity of 100 % IACS as well as no susceptibility for hydrogen embrittlement. Due to the absence of oxides in the structure, Cu-OF is capable of withstanding extra deep drawing and severe forming and is superior to Cu-ETP in this respect. Cu-OFE is favoured for very critical electrical, electronic and communication applications.

#### Composition

Cu*	O <sub>2</sub>		
[%]	(ppm)		
99.95 min	10 max		

\*) Incl. Ag

## Physical properties

Melting point	Density	Specific heat cap. at 20°C	Electrical cond.	Thermal cond. at 20°C	Mod. of elasticity	Coef. of therm exp. at 20°C [10 <sup>-6</sup> /°F]	
[°F]	[lb/in³]	[Btu/lb°F]	[%IACS]	[Btu/ft h °F]	x1000 ksi	[10 <sup>-6</sup> /K]	
[°C]	[g/cm³]	[kJ/kgK]	[MS/m]	[W/mK]	[GPa]		
<b>1981</b>	<b>0.323</b>	0.092	<b>100</b>	<b>226</b>	<b>17</b>	9.8	
1083	8.90	0.394	58	391	117	17.6	

The specified conductivity applies to the soft condition only

# Mechanical properties

	Tensile strength Rm	Yield strength Rp0.2 nominal	Elon- gation 2" nominal	nominal nal HR30T	min bend ratio 90°		min. bend ratio 180°	
	[ksi] [MPa]	[ksi] [MPa]	[%]	HV	GW	BW	GW	BW
Soft	<b>26-38</b> 179-262	<b>10</b> 69	35		0.0	0.0	0.0	0.0
H02 (1/2H)	<b>37-46</b> 255-317	<b>37</b> 255	20	<b>50</b> 90	0.0	0.5	0.0	1.0
H04 (H)	<b>43-52</b> 297-359	<b>45</b> 310	8	<b>58</b> 100	1.0	2.0	2.0	3.0
H06 (EH)	<b>47-56</b> 324-386	<b>50</b> 349	3	<b>60</b> 105	2.0	3.0	2.5	
H08 (SH)	<b>50-58</b> 345-400	<b>52</b> 359	3	<b>63</b> 110	3.0		4.0	
H10 (ES)	<b>52 min</b> 359 min	<b>54</b> 373	2	<b>61 min</b> 112 min				

Other tempers are available upon request.

GW bend axis transverse to rolling direction. BW bend axis parallel to rolling direction



## Fabrication properties

Electrical and thermal conductivity	superior
Corrosion resistance	excellent
Resistance to hydrogen embrittlement	good
Cold formability	good

### Typical uses

Telecommunication cables, electrical and electronic conductors, contacts and terminals, printed circuits, carrier tapes, flexible circuits, terminal lugs

## Applicable specifications

ASTM B152, ASME SB152